

## VeroUltraClear

VeroUltraClear™ is a transparent PolyJet™ digital material offering exceptional clarity combined with strength, stiffness and impact resistance. VeroUltraClear simulates PMMA (polymethyl methacrylate), commonly known as acrylic, achieving 86% light transmission through a 6 mm thick sample. VeroUltraClear has a higher level of clarity and transparency and a lower yellow index than standard VeroClear™. Thermal properties are similar but mechanical properties are somewhat lower than VeroClear.

Typical applications include concept models and prototypes for eyewear, lighting components, and the replication of glass and clear polymers. Other uses include modeling clear tubes and housings for pumps and gearboxes to view fluid flow and internal mechanisms.

	ASTM	Value	
Tensile Strength	D-638-03	39 - 43 MPa (5,650 - 6,240 psi)	
Elongation at Break	D-638-05	20 – 35%	
Modulus of Elasticity	D-638-04	1,400 - 2,100 MPa (203,000 - 304,600 psi)	
Flexural Strength	D-790-03	58 – 72 MPa (8,400 – 10,400 psi)	
Flexural Modulus	D-790-04	1,900 - 2,300 MPa (275,000 - 333,000 psi)	
HDT, °C @ 0.45 MPa Before Photobleaching	D-648-06	47 – 49 °C (117 – 120 °F)	
HDT, °C @ 0.45 MPa After Photobleaching	D-648-06	48 – 52 °C (118 – 126 °F)	
Izod Notched Impact	D-256-06	20 - 30 J/m (0.375 - 0.562 ft-lb/in.)	
Water Absorption	D-570-98 24hr	1.25 – 1.40%	
Tg	DMA, E»	52 – 54 °C (125.6 – 129.2 °F)	
Shore Hardness	Scale D	80 – 85	
Rockwell Hardness	Scale M	70 – 75	
Polymerized Density	ASTM D792	1.18 – 1.19 g/cm <sup>3</sup>	
Ash Content	USP 281	0.02 - 0.06%	

System Availability				
Printer	Minimum Layer Thickness	Support Structure	Available Colors	
J835™ / J850™	14 microns (0.00055 in.)	SUP705 (water jet removable) SUP706B (soluble)	Clear	

## Stratasys Headquarters

7665 Commerce Way, Eden Prairie, MN 55344 USA +1 952 937 3000 (international) +1 952 937 0070 (Fax)

stratasys.com ISO 9001:2008 Certifi ed Stratasys GmbH Airport Boulevard B120 77836 Rheinmünster, Germany +49 7229 7772-0 +49 7229 7772-990 (Fax)



